

Abstract of the Disclosure

- 5        An insulating material is constructed in weight percent from about 20-60% low melt bicomponent fiber, 10-40% high melt bicomponent fiber and 20-60% staple fiber. The material provides a unique combination of strength, acoustical insulating and even thermal insulating properties heretofore unavailable in the art.